

Content

Test Report	3
1 Emission test	3
1.1 Volatile Organic Compounds (VOC)	3
Measurement time 3 days after test chamber loading	7
1.1.1 CMR-VOC _{3d}	7
1.1.2 VOC / TVOC _{3d}	8
1.1.3 SVOC _{3d}	10
1.1.4 VVOC _{3d}	11
1.1.4.1 Formaldehyde _{3d} and Acetaldehyde _{3d}	12
Measurement time 28 days after test chamber loading	13
1.1.5 CMR-VOC _{28d}	13
1.1.6 VOC / TVOC _{28d}	14
1.1.7 SVOC _{28d}	16
1.1.8 VVOC _{28d}	17
1.1.8.1 Formaldehyde _{28d} and Acetaldehyde _{28d}	18
2 Odour	19
3 Content analysis	20
3.1 Organic halogenated compounds (AOX / EOX) *	20
3.2 Heavy Metals *	21
3.3 Organotin compounds	22
3.4 Phthalates	23
Evaluation	24
Summary evaluation	26

Sample view

Internal Sample-no.	Description by customer	Condition upon delivery	Type of sample
A001	Thermalife Interior	without objection	Wall color

Test Report

1 Emission test

1.1 Volatile Organic Compounds (VOC)

Definition of terms:

VOC (volatile organic compounds)	All individual materials with a concentration $\geq 0,001 \text{ mg/m}^3$ in retention range C_6 (n-Hexane) to C_{16} (n-Hexadecane) Substances refer to LCI lists / AgBB (DIBt)
TVOC (Total volatile organic compounds)	Sum of all individual substances in retention range C_6 to C_{16} .
CMR-VOC (carcinogenic, mutagenic, reproduction-toxic VOC, VVOC and SVOC)	All individual substances with the following categories: Regulation (EC) No. 1272/2008: Category Car.1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B TRGS 905: K1 and K2, M1 and M2, R1 and R2 IARC: Group 1 and 2A DFG (MAK lists): Category III1and III2
VVOC (very volatile organic compounds)	All individual substances wit concentration $\geq 0,001 \text{ mg/m}^3$ in retention range $< C_6$
TVVOC (Total very volatile organic compounds)	Sum of all VVOC in retention range $< C_6$
SVOC (semi volatile organic compounds)	All individual materials $\geq 0,001 \text{ mg/m}^3$ in retention range $> C_{16}$ (n-Hexadecane) to C_{22} (Docosane)
TSVOC (Total semi volatile organic compounds)	Sum of all SVOC in retention range $> C_{16}$ to C_{22} .
Identified and calibrated substances ($C_{id \text{ sub}}$), substance specific calculated	Spectrum and retention time are concordant with the calibrated comparison substance
Not identified substances calculated as toluene equivalent ($C_{ni \text{ tol}}$)	Suggestion from the spectrum library with high probability and/or allocation to a group of substances
SER	Specific emission rate (see appendix)
LCI value	Lowest Concentration of Interest; calculated value for the evaluation of VOC, established by the Committee for Health-related Evaluation of Building Products (Ausschuss zur gesundheitlichen Bewertung von Bauprodukten - AgBB)
R value	The quotient of the concentration and the LCI value is generated for every substance which is detected in the test chamber air. The sum of the calculated quotients results in the R value.

List of analysed VOCs:**Aromatic hydrocarbons**

Toluene
Ethylbenzene
p-Xylene
m-Xylene
o-Xylene
Isopropylbenzene
n-Propylbenzene
1,3,5-Trimethylbenzene
1,2,4-Trimethylbenzene
1,2,3-Trimethylbenzene
2-Ethyltoluene
1-Isopropyl-4-methylbenzene
1,2,4,5-Tetramethylbenzene
n-Butylbenzene
1,3-Diisopropylbenzene
1,4-Diisopropylbenzene
Phenyl octane
1-Phenyl decane²
1-Phenyl undecane²
4-Phenylcyclohexene
Styrene
Phenyl acetylene
2-Phenyl propene
Vinyl toluene
Naphthalene
Indene
Benzene
Cresol

Saturated aliphatic substances

Hydrocarbons
2-Methyl pentane¹
3-Methyl pentane¹
n-Hexane
Cyclohexane
Methylcyclohexane
n-Heptane
n-Octane
n-Nonane
n-Decane
n-Undecane
n-Dodecane
n-Tridecane
n-Tetradecane
n-Pentadecane
n-Hexadecane
Methylcyclopentane
1,4-Dimethylcyclohexane

Terpenes

δ-3-Carene
α-Pinene
β-Pinene
Limonene
Longifolene
Caryophyllene
Isolongifolene
alpha-Phellandrene
Myrcene
Camphene
alpha-Terpinend
Longipinene
beta-Caryophyllene
beta-Farnesen
alpha-Bisabolen

Aliphatic alcohols and ether

1-Propanol¹
2-Propanol¹
tert-Butanol
2-Methyl-1-propanol

1-Butanol
1-Pentanol
1-Hexanol
Cyclohexanol
2-Ethyl-1-hexanol
1-Octanol
4-Hydroxy-4-methyl-pentan-2-one
1-Heptanol
1-Nonanol
1-Decanol

Aromatic alcohols (phenols)

Phenol
BHT (2,6-di-tert-butyl-4-methylphenol)
Benzylalcohol

Glycols, Glycol ether, Glycol ester

Propylenglycol (1,2-Dihydroxypropane)
Ethylene glycol (Ethandiol)
Ethylene glycol monobutyl ether
Diethylene glycol
Diethylene glycol-monobutyl ether
2-Phenoxyethanol
Ethylene carbonate
1-Methoxy-2-propanol
Glycolic acid butyl ester
Texanol
Butyldiglycol acetate
Dipropylenglycol mono-methyl ether
2-Methoxyethanol
2-Ethoxyethanol
2-Propoxyethanol
2-Methylethoxyethanol
2-Hexoxyethanol
1,2-Dimethoxyethane
1,2-Diethoxyethane
2-Methoxyethyl acetate
2-Ethoxyethyl acetate
2-Butoxyethyl acetate
2-(2-Hexoxyethoxy)-ethanol
1-Methoxy-2-(2-methoxy-ethoxy)-ethane
Propylene glycol di-acetate
Dipropylene glycol
Dipropylene glycol
monomethylether acetate
Dipropylene glycol mono-n-propylether
1,4-Butanediol
Tripropyleneglycolmonomethyl ether
Triethylene glycol dimethyl ether
1,2-Propylene glycol dimethyl ether
TXIB
Ethylidiglycol
Dipropylene glycol-dimethyl ether
Propylene carbonate
Hexylene glycol
3-Methyl-1-butanol
1,2-Propylene glycol n-propyl ether
1,2-Propylene glycol n-butyl ether
Diethylglycol phenyl ether
Neopentyl glycol

Aldehydes

Butanal^{1,3}
Pentanal³
Hexanal
Heptanal
2-Ethylhexanal
Octanal
Nonanal
Decanal
2-Butenal³

2-Pentenal³
2-Hexenal
2-Heptenal
2-Octenal
2-Nonenal
2-Decenal
2-Undecenal
Furfural
Glutaraldehyde
Benzaldehyde
Acetaldehyde^{1,3}
Propanal^{1,3}
Propenal^{1,3}
Isobutanol
3-Methyl-2-propanol
Methylisobutylketone
Cyclopentanone
Cyclohexanone

Ketones

Ethylmethylketone³
3-Methyl-2-propanol
Methylisobutylketone
Cyclopentanone
Cyclohexanone
Acetone^{1,3}
2-Methylcyclopentanone
2-Methylcyclohexanone
Acetophenone
1-Hydroxyacetone

Acids

Acetic acid
Propionic acid
Isobutyric acid
Butyric acid
Pivalic acid
n-Valeric acid
n-Hexanoic acid
n-Heptanoic acid
n-Octanoic acid
2-Ethylhexanoic acid

Esters and Lactones

Methylacetate¹
Ethyl acetate¹
Vinyl acetate¹
Isopropyl acetate
Propyl acetate
2-Methoxy-1-methylethyl acetate
n-Butyl formate
Methylmethacrylate
Isobutylacetate
1-Butyl acetate
2-Ethylhexyl acetate
Methyl acrylate
Ethyl acrylate
n-Butyl acrylate
2-Ethylhexyl acrylate
Adipic acid dimethyl ester
Fumaric acid dibutyl ester
Succinic acid dimethyl ester
Hexandioldiacrylate
Maleic acid dibutyl ester
Butyrolactone
Dibutyl glutarate
Dibutyl succinate
Dimethylphthalate
Texanol
Dipropylene glycol diacrylate

Chlorinated hydrocarbons

Tetrachlorethene
1,1,1-Trichlorethane
Trichlorethene
1,4-Dichlorbenzene

Others

1,4-Dioxane
Caprolactam
N-Methyl-2-pyrrolidone
Octamethylcyclotetrasiloxane
Methenamine
2-Butanonoxime
Triethyl phosphate
5-Chlor-2-methyl-4-isothiazolin-3-one
2-Methyl-4-isothiazolin-3-one (MIT)
Triethylamine
Decamethylcyclopentasiloxane
Dodecamethylcyclopentasiloxane
Tetrahydrofuran (THF)
1-Decene
1-Octene
2-Pentylfuran
Tetramethyl succinonitrile
Propylencarbonate
Isophorone
Dimethylformamide (DMF)
Tributyl phosphate

1 VOC

2 SVOC

3 Analysis according to
DIN ISO 16000-3

Explanation of the Specific Emission Rate SER

Emission measurements are accomplished in test chambers under defined physical conditions (temperature, relative humidity, room loading, air change rate etc.).

Test chamber measurement results are directly comparable only if the investigations were accomplished under the same basic conditions.

If the differences of the physical conditions refer only to the change of air rate and/or the loading, the "SER" or "specific emission rate" can be used for comparability of the measurement results. The SER indicates how many volatile organic compounds (VOC) are released by the sample for each material unit and hour (h). The SER can be calculated using the formula below for each proven individual component of the VOC from the data in the test report.

As material units the following are applicable:

l = unit of length (m)	relation between emission and length
a = unit area (m ²)	relation between emission and surface
v = unit volume (m ³)	relation between emission and volume
u = piece unit (unit = piece)	relation between emission and complete unit

From this the different dimensions for SER result:

length-specific	SER _l in µg/m h
surface-specific	SER _a in µg/m ² h
volume-specific	SER _v in µg/m ³ h
unit specific	SER _u in µg/u h

SER thus represents a product specific rate, which describes the mass of the volatile organic compound, which is emitted by the product per time unit at a certain time after beginning of the examination.

$$\boxed{\text{SER} = q \cdot C}$$

q	specific air flow rate (quotient from change of air rate and loading)
C	Concentration of the measured substance(s)

The result can be indicated in milligrams (mg) in place of micro grams (µg), whereby 1 mg = 1000 µg.

Test method

Preparation of test sample:	Date:	22.02.2013
	Pre-treatment:	Product was applied at a glass plate; application rate: 0,2 – 0,3 l/m ² (12,7 g); drying: 4 h
	Masking of backside:	not applicable
	Masking of edges:	not applicable
	Relationship of unmasked edges to surface:	not applicable
	Charging:	related to area
	Dimensions:	2 x [25 cm x 25 cm]
Test chamber conditions::	Chamber volume:	0,125 m ³
	Temperature:	23 °C
	Relative humidity:	50 %
	Air pressure:	normal
	Air:	cleaned
	Air change rate:	0.5 h ⁻¹
	Air velocity:	0,3 m/s
	Loading:	1 m ² /m ³
	Specific air flow rate:	0.5 m ³ /m ² · h
	Air sampling:	3 and 28 days after test chamber loading
Analytics:	DIN ISO 16000-3	
	DIN ISO 16000-6	
	Limit of determination:	1 µg/m ³

Measurement time 3 days after test chamber loading

1.1.1 CMR-VOC_{3d}

Test parameter:

Carcinogenic, mutagenic and reproduction-toxic volatile organic compounds (CMR VOC), test chamber, air sampling 3 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS No.	Concentration (Test chamber air) [µg/m³]	CMR classifica- tion*)
VOC_{3d}: Identified and calibrated substances in accordance with LCI list/AgBB, substance specific calculated (c_{id sub})				
-	-	-	-	n.d.
VOC_{3d}: Further identified and calibrated CMR substances in addition to LCI list/AgBB, substance specific calculated (c_{id sub})				
-	-	-	-	n.d.
VOC_{3d}: Further identified, not calibrated CMR substances, calculated as toluene equivalent (c_{ni tol})				
-	-	-	-	n.d.

*) Classification acc. to Regulation (EC) No. 1272/2008: Category Carc. 1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B, TRGS 905: K1 and K2, M1 and M2, R1 and R2, IARC: Group 1 and 2A, DFG (MAK list): Category III1 and III2

	Concentration (Test chamber air) [µg/m³]	SER _a [µg/m²h]
Sum of VOC with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B TRGS 905: K1 and K2, M1 and M2, R1 and R2 IARC: Group 1 and 2A DFG (MAK list): Category III1 and III2	n.d.	n.d.

n.d. = not detectable

1.1.2 VOC / TVOC_{3d}**Test parameter:**

Volatile organic compounds (VOC), test chamber, air sampling 3 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS No.	Concentration (Test chamber air) [$\mu\text{g}/\text{m}^3$]
VOC_{3d}: Identified and calibrated substances in accordance with LCI list/AgBB, substance specific calculated ($c_{\text{id sub}}$)			
1	Aromatic hydrocarbons		
1-1	Toluene	108-88-3	6
3-5.4	alpha-Phellandrene	99-83-2	
4	Aliphatic alcohols and ethers		
4-10	2-Ethyl-1-hexanol	104-76-7	9
6	Glycols, Glycol ethers, Glycol esters		
6-1	Propylenglycol (1,2-Dihydroxypropane)	57-55-6	
6-2	Ethylene glycol (Ethandiol)	107-21-1	2600
6-31	Dipropylene glycol mono-n-butyl ether	29911-28-2	1
10	Esters and Lactones		
10-16	2-Ethylhexyl acrylate	103-11-7	2
12	Others		
12-5	Methenamine	100-97-0	3
12-10	2-Methyl-4-isothiazolin-3-one (MIT)	2682-20-4	76
VOC_{3d}: Further identified and calibrated substances in addition with LCI list/AgBB, substance specific calculated ($c_{\text{id sub}}$)			
12	Others		
-	Hexamethylcyclotrisiloxan	09.05.541	2
-	Benzothiazol	95-16-9	1
VOC_{3d}: Not calibrated substances calculated as toluene equivalent ($c_{\text{ni tol}}$)			
-	Not identified	-	2
-	Not identified, probably Ester	-	2
-	Several aromatic compounds	-	17
-	Siloxane comound	-	4
-	Not identified	-	1
-	Isoalkane, C9-C10	-	2
-	Several aromatic compounds	-	5

Remark: The test result referred to the submitted test sample exclusively. The validity of the report is three years at most and will end immediately at any alternation of material composition or in manufacturing process. Publishing in parts requires authorisation.

Total volatile organic compounds	Concentration (test chamber air) [µg/m³]	SER_a [µg/m²h]
TVOC_{3d}	2734	1367

Further VOC sums	Concentration (test chamber air) [µg/m³]	SER_a [µg/m²h]
Sum VOC without LCI	36	18
Sum of bicyclic terpenes	n.d.	n.d.
Sum of sensitising materials with the following categorisations: DFG (MAK lists): Category IV German Federal Institute for Risk Assessment lists: Cat A TRGS 907	2	1
Sum of VOC with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 2, Muta. 2, Repr. 2 TRGS 905: K3, M3, R3 IARC: Group 2B DFG (MAK list): Category III3	10	5
C₉ - C₁₄ - Alkanes / Isoalkanes	1	1
Sum C₄-C₁₁ Aldehydes, acyclic, aliphatic	n.d.	n.d.

R-Value (without dimension)_{3d}	10,99
---	--------------

n.d. = not detectable

1.1.3 SVOC_{3d}**Test parameter:**

Semivolatile organic compounds (SVOC), test chamber, air sampling 3 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS No.	Concentration (test chamber air) [µg/m ³]
SVOC_{3d}: Identified and calibrated substances in accordance with LCI list/AgBB, substance specific calculated(c_{id sub})			
-	-	-	n.d.
SVOC_{3d}: Further identified and calibrated substances in addition to LCI list/AgBB, substance specific calculated(c_{id sub})			
-	-	-	n.d.
SVOC_{3d}: Not calibrated substances calculated as toluene equivalent (c_{ni tol})			
-	Siloxane compound	-	1

Total semivolatile organic compounds	Concentration (test chamber air) [µg/m ³]	SER _a [µg/m ² h]
TSVOC_{3d}	1	1

n.d. = not detectable

1.1.4 VVOC_{3d}

Test Parameter:

Very volatile organic compounds (VVOC), test chamber, air sampling 3 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS-No.	Concentration (test chamber air) [µg/m³]
VVOC_{3d}: Identified and calibrated substances in accordance with LCI list/AgBB, substance specific calculated(c_{id sub})			
4	Aliphatic alcohols and ethers		
4-2	1-Propanol	71-23-8	1
4-3	2-Propanol	67-63-0	1
7	Aldehydes		
7-20	Acetaldehyde	75-07-0	3
VVOC_{3d}: Further identified and calibrated substances in addition to LCI list/AgBB, substance specific calculated(c_{id sub})			
-	-	-	n.d.
VVOC_{3d}: Not calibrated, identified substances calculated as toluene equivalent (c_{ni tol})			
-	-	-	n.d.

Total very volatile organic compounds	Concentration (test chamber air) [µg/m³]	SER _a [µg/m²h]
TVVOC_{3d}	5	3

n.d. = not detectable

1.1.4.1 Formaldehyde_{3d} and Acetaldehyde_{3d}**Test parameter:**

Formaldehyde and Acetaldehyde, test chamber, air sampling 3 days after test chamber loading

Test method:

Preparation of test sample and Test chamber conditions:	see Volatile organic compounds
Analytics:	DIN ISO 16000-3
Limit of determination:	3 µg/m ³ ≈ 0,003 ppm

Test result:

Sample:	A001: Thermalife Interior
---------	---------------------------

Substance	Concentration (Test chamber air) [µg/m ³]	Concentration (Test chamber air) [ppm]
Formaldehyde	88	0,071
Acetaldehyde	3	-

Measurement time 28 days after test chamber loading

1.1.5 CMR-VOC_{28d}

Test parameter:

Carcinogenic, mutagenic and reproduction-toxic volatile organic compounds (CMR VOC), test chamber, air sampling 28 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS No.	Concentration (Test chamber air) [µg/m³]	CMR classifica- tion*)
VOC_{28d}: Identified and calibrated substances in accordance with LCI list/AgBB, sub- stance specific calculated (c_{id sub})				
-	-	-	-	n.d.
VOC_{28d}: Further identified and calibrated CMR substances in addition to LCI list/AgBB, substance specific calculated(c_{id sub})				
-	-	-	-	n.d.
VOC_{28d}: Further identified, not calibrated CMR substances, calculated as toluene equiva- lent (c_{ni tol})				
-	-	-	-	n.d.

*) Classification acc. to Regulation (EC) No. 1272/2008: Category Carc. 1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B, TRGS 905: K1 and K2, M1 and M2, R1 and R2, IARC: Group 1 and 2A, DFG (MAK list): Category III1 and III2

	Concentration (Test chamber air) [µg/m³]	SER _a [µg/m²h]
Sum of VOC with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B TRGS 905: K1 and K2, M1 and M2, R1 and R2 IARC: Group 1 and 2A DFG (MAK list): Category III1 and III2	n.d.	n.d.

n.d. = not detectable

1.1.6 VOC / TVOC_{28d}**Test parameter:**

Volatile organic compounds (VOC), test chamber, air sampling 28 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS No.	Concentration (Test chamber air) [$\mu\text{g}/\text{m}^3$]
VOC_{28d}: Identified and calibrated substances in accordance with LCI list/AgBB, substance specific calculated ($c_{\text{id sub}}$)			
4	Aliphatic alcohols and ethers		
4-10	2-Ethyl-1-hexanol	104-76-7	5
VOC_{28d}: Further identified and calibrated substances in addition with LCI list/AgBB, substance specific calculated ($c_{\text{id sub}}$)			
12	Others		
-	Hexamethylcyclotrisiloxan	-	2
VOC_{28d}: Not calibrated substances calculated as toluene equivalent ($c_{\text{ni tol}}$)			
-	Not identified compound	-	1

Total volatile organic compounds	Concentration (test chamber air) [$\mu\text{g}/\text{m}^3$]	SER _a [$\mu\text{g}/\text{m}^2\text{h}$]
TVOC_{28d}	8	4

Remark: The test result referred to the submitted test sample exclusively. The validity of the report is three years at most and will end immediately at any alternation of material composition or in manufacturing process. Publishing in parts requires authorisation.

Further VOC sums	Concentration (test chamber air) [µg/m³]	SER _a [µg/m²h]
Sum VOC without LCI	3	2
Sum of bicyclic terpenes	n.d.	n.d.
Sum of sensitising materials with the following categorisations: DFG (MAK lists): Category IV German Federal Institute for Risk Assessment lists: Cat A TRGS 907	n.d.	n.d.
Sum of VOC with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 2, Muta. 2, Repr. 2 TRGS 905: K3, M3, R3 IARC: Group 2B DFG (MAK list): Category III3	3	2
C₉ - C₁₄ - Alkanes / Isoalkanes	n.d.	n.d.
Sum C₄-C₁₁ Aldehydes, acyclic, aliphatic	n.d.	n.d.

R-Value (without dimension)_{28d}	0,01
--	-------------

n.d. = not detectable

1.1.7 SVOC_{28d}**Test parameter:**

Semivolatile organic compounds (SVOC), test chamber, air sampling 28 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS No.	Concentration (test chamber air) [µg/m ³]
SVOC_{28d}: Identified and calibrated substances in accordance with LCI list/AgBB, substance specific calculated($c_{id\ sub}$)			
-	-	-	n.d.
SVOC_{28d}: Further identified and calibrated substances in addition to LCI list/AgBB, substance specific calculated($c_{id\ sub}$)			
-	-	-	n.d.
SVOC_{28d}: Not calibrated substances calculated as toluene equivalent ($c_{ni\ tol}$)			
-	-	-	n.d.

Total semivolatile organic compounds	Concentration (test chamber air) [µg/m ³]	SER _a [µg/m ² h]
TSVOC_{28d}	n.d.	n.d.

n.d. = not detectable

1.1.8 VVOC_{28d}**Test Parameter:**

Very volatile organic compounds (VVOC), test chamber, air sampling 28 days after test chamber loading

Test result:

Sample: A001: Thermalife Interior

No.	Substance	CAS-No.	Concentration (test chamber air) [µg/m³]
VVOC_{28d}: Identified and calibrated substances in accordance with LCI list/AgBB, substance specific calculated(c_{id sub})			
7	Aldehydes		
7-20	Acetaldehyde	75-07-0	3
VVOC_{28d}: Further identified and calibrated substances in addition to LCI list/AgBB, substance specific calculated(c_{id sub})			
-	-	-	n.d.
VVOC_{28d}: Not calibrated, identified substances calculated as toluene equivalent (c_{ni tol})			
-	-	-	n.d.

Total very volatile organic compounds	Concentration (test chamber air) [µg/m³]	SER _a [µg/m²h]
TVVOC_{28d}	3	2

n.d. = not detectable

1.1.8.1 Formaldehyde_{28d} and Acetaldehyde_{28d}**Test parameter:**

Formaldehyde and Acetaldehyde, test chamber, air sampling 28 days after test chamber loading

Test method:

Preparation of test sample and Test chamber conditions:	see Volatile organic compounds
Analytics:	DIN ISO 16000-3
Limit of determination:	3 µg/m ³ ≈ 0,003 ppm

Test result:

Sample:	A001: Thermalife Interior
---------	---------------------------

Substance	Concentration (Test chamber air) [µg/m ³]	Concentration (Test chamber air) [ppm]
Formaldehyde	24	0,019
Acetaldehyde	3	-

2 Odour

Test parameter:

Odour, testing collective, odour testing, hours after loading of desiccator

Test method:

Manufacture of test specimen:	see 1.1 volatile organic compounds
Conditions of desiccator:	Temperature: 23°C Relative air humidity: 50% Loading: See 1.1 volatile organic compounds Air sampling: hours after loading of desiccator
Analytics:	following VDA-recommendation 270
Ratings:	1 not perceptible 2 perceptible, not bothering 3 clearly perceptible, not bothering 4 bothering 5 strongly bothering 6 unbearable

Test result:

Sample:	A001: MIG-ESP Interior
---------	------------------------

Intensity of odour
1 - 2

3 Content analysis

3.1 Organic halogenated compounds (AOX / EOX) *

Test parameter:

Absorbable organic halogenated compounds (AOX) and extractable organic halogenated compounds (EOX)

Test method:

Analytiks::	AOX: elution with purest water in Soxleth-apparatus, mixing of 50 ml of the elution with 50 mg activated carbon, combustion of organic bound halogens in oxygen flow, micro coulometric determination of halogen content EOX: clean up on silica gel, extraction with ethyl acetate, combustion of extract in oxygen flow, micro coulometric determination of halogen content
Limit of determination:	AOX: 0,5 mg/kg, EOX: 2 mg/kg

Test result:

Sample:	Parameter	Content (Material) [mg/kg]
A001: MIG-ESP Interior	AOX	< 0.5
	EOX	< 2.0

3.2 Heavy Metals *

Test Parameter:

Heavy Metals

Test Method:

Analytics:

Total decomposition in microwave with nitric acid
Analysis according to DIN 17294-2.

Limit of determination:

See above

Test result:

Sample:

A001: Thermalife Interior

Parameter	content (material) [mg/kg]	limit of determination: [mg/kg]
Arsenic (As)	< 0,5	0,5
Cadmium (Cd)	< 0,2	0,2
Chromium (Cr)	< 1	1
Mercury (Hg)	< 0,1	0,1
Nickel (Ni)	2	1
Lead (Pb)	4	0,5
Tin (Sn)	< 1	1

Remark: The test result referred to the submitted test sample exclusively. The validity of the report is three years at most and will end immediately at any alternation of material composition or in manufacturing process. Publishing in parts requires authorisation.

3.3 Organotin compounds

Test parameter:

Organotin compounds

Test method:

Analytics: Extraction, analysis following DIN EN ISO 17353

Limit of determination: 0,025 mg/kg

Test result:

Sample	Parameter	Content (Material) [mg/kg]
A001: MIG-ESP Interior	Monobutyltin (MBT)	< 0.025
	Dibutyltin (DBT)	< 0.025
	Tributyltin (TBT)	< 0.025
	Monooctyltin (MOT)	< 0.025
	Dioctyltin (DOT)	< 0.025
	Triphenyltin (TPhT)	< 0.025

3.4 Phthalates

Test parameter:

Phthalates

Test method:

Analytics:

Following DIN EN 15777 (modified acc. to DIN EN ISO 14389)


Limits of determination:

All: 4 mg/kg
 but DINP, DIDP: 30 mg/kg
 DIHP: 50 mg/kg
 DHNUP: 100 mg/kg

Test result:

Sample	Parameter	Result (Material) [mg/kg]
A001: ECODECO wallcovering	Dimethylphthalate (DMP)	< 3
	Diethylphthalate (DEP)	< 3
	Dipropylphthalate (DPrP)	< 3
	Dibutylphthalate (DBP)	< 3
	Benzylbutylphthalate (BBP)	< 3
	Diethylhexylphthalate (DEHP)	4
	Di-n-octylphthalate (DNOP)	< 3
	Di-iso-butylphthalate (DIBP)	< 3
	Bis(2-methoxyethyl)phthalate (BMEP)	< 3
	Di-n-hexylphthalate (DHP)	< 3
	Dipentylphthalat (DPP)	< 3
	Di-iso-nonylphthalate (DINP)	< 30
	Di-iso-decylphthalate (DIDP)	< 30
	Di(C6-C8-alkyl)phthalate branched (DIHP)	< 50
	Di(C7-C11-alkyl)phthalate linear+branched (DHNUP)	< 100
	Sum	4

Cologne, 26.03.2013



Dr. rer.-nat. Hans-Ulrich Krieg
 (Technical Manager)

Remark: The test result referred to the submitted test sample exclusively. The validity of the report is three years at most and will end immediately at any alternation of material composition or in manufacturing process. Publishing in parts requires authorisation.

Evaluation

The product **MIG-ESP Interior** was submitted to laboratory tests on behalf of MIG Material Innovative Gesellschaft mbH for an ecological product examination according to the eco-INSTITUT-Label test criteria "Painting and coating materials" (status: September 2010).

The results documented in the test report were evaluated as follows.

Test parameter	Result	Limit value	Within limits [yes/no]
Emission test			
Measurement time: 3 days after test chamber loading			
TVOC (total volatile organic compounds)	2734 µg/m³	≤ 300 µg/m³	yes
VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B; TRGS 905: K1, K2, M1, M2, R1, R2; IARC: Group 1 and 2A; DFG (MAK list): Categories III1, III2	< 1 µg/m³	≤ 1 µg/m³	yes
Measurement time: 28 days after test chamber loading			
TVOC (total volatile organic compounds)	8 µg/m³	≤ 300 µg/m³	yes
VOC (sum) without NIK	3 µg/m³	≤ 100 µg/m³	yes
VOC (individual values):			
Sum of bicyclic terpenes	< 1 µg/m³	≤ 200 µg/m³	yes
Sum of sensitising materials with the following categorisations: DFG (MAK list): Category IV, German Federal Institute for Risk Assessment lists: Cat A, TRGS 907	< 1 µg/m³	≤ 100 µg/m³	yes
Sum of VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 2, Muta. 2, Repr. 2; TRGS 905: K3; IARC: Group 2B; DFG (MAK list): Category III3	3 µg/m³	≤ 50 µg/m³	yes
Sum C9 – C14: Alkanes / Isoalkanes	< 1 µg/m³	≤ 200 µg/m³	yes
Sum C4 – C11 Aldehydes, acyclic, aliphatic	< 1 µg/m³	≤ 100 µg/m³	yes
VOC (individual substances):			
Styrene	< 1 µg/m³	≤ 10 µg/m³	yes
Methylisothiazolinone (MIT)	< 1 µg/m³	n.d.	yes
Benzaldehyde	< 1 µg/m³	≤ 20 µg/m³	yes
TSVOC (total semi-volatile organic compounds)	< 1 µg/m³	≤ 100 µg/m³	yes
R value	0,01	≤ 1,0	yes
Formaldehyde	24 µg/m³	≤ 24 µg/m³	yes
Acetaldehyde	3 µg/m³	≤ 24 µg/m³	yes
Odour	Grade 1- 2	≤ Grade 3 (24 hours after loading of desiccator)	yes

Remark: The test result referred to the submitted test sample exclusively. The validity of the report is three years at most and will end immediately at any alternation of material composition or in manufacturing process. Publishing in parts requires authorisation.

Test parameter	Result	Limit value	Within limits [yes/no]
Content analysis			
AOX (adsorbable organic halogenated compounds)	< 1 mg/kg	≤ 1,0 mg/kg	yes
EOX (extractable organic halogenated compounds)	< 2 mg/kg	≤ 2,0 mg/kg	yes
Heavy Metals			
Arsenic (As)	< 0,5 mg/kg	≤ 5,0 mg/kg	yes
Cadmium (Cd)	< 0,2 mg/kg	≤ 0,5 mg/kg	yes
Chromium (Cr)	< 1 mg/kg	≤ 20,0 mg/kg	yes
Mercury (Hg)	< 0,1 mg/kg	≤ 0,2 mg/kg	yes
Nickel (Ni)	1 mg/kg	≤ 20,0 mg/kg	yes
Lead (Pb)	6 mg/kg	≤ 20,0 mg/kg	yes
Tin (Sn)	< 1 mg/kg	≤ 5,0 mg/kg	yes
Organotin compounds (limit value per single substance) TBT, DBT, TPhT, MBT, MOT, DOT	all < 0.025 mg/kg	≤ 0,05 mg/kg	yes
Phthalates (Sum) DMP, DEP, DPrP, DBP, BBP, DEHP, DNOP, DIDP, BMEP, DHP, DPP, DINP, DIDP, DIHP, DHNUP	4 mg/kg	≤ 500 mg/kg	yes